

#### ■ DESCRIPTION

**Primer 2001** is a primer containing isocyanates.

#### ■ USES

- **Primer 2001** may be used on different substrates (concrete, aluminium, wood, glass, plastics) to improve the adhesion of others sealants. Seals off the porosity of materials such as wood or concrete, thus reducing or preventing problems of bubbling under severe conditions.
- May also be used as a barrier between sealant and paint to prevent migration of plasticizers.

#### ■ SURFACE PREPARATION

Substrate preparation :

- The substrates to be assembled must be dry, dust free and not have any traces of grease or other contaminants that could adversely affect the bonding performance.
- If the substrates need to be cleaned, solvents such as **Primer 2001**, methylethylketone (MEK) or acetone may be used. For substrates sensitive to ketones, use **Primer 2001**.
- The use of solvents must comply with local regulations. Check the compatibility of the solvent used with the substrates.
- If necessary, rub down metal surfaces beforehand. After rubbing down, the surface should be recleaned. Allow the substrate to dry after degreasing. We recommend that concrete be cleaned with a metal brush.

**Note:** when using solvents, extinguish all sources of ignition and carefully follow the safety and handling instructions given by the manufacturer or supplier.

#### ■ APPLICATION

- **Primer 2001** may be applied by a lint-free applicator pad or brush between 5 and 40°C.
- Thoroughly homogenise before application.
- This product should be used within 24 hours of opening the protective seal on the bottle.
- Close after every use (any contact with moisture will cause the product to cure).
- If applied in cold weather, store the packagings at 20°C before use.
- After drying, apply the sealant within a one hour deadline, proceeding according to instructions of its technical data sheet.



**PRIMER 2001**



#### ■ PACKAGING

30 and 250 g bottles;  
1 kg cans;  
5.2 and 10 kg buckets;  
200 L drums.

#### ■ TYPICAL PROPERTIES

**Color:** Pale yellow transparent

**Viscosity:** Brookfield RVT spindle 2 / 100 rpm:  
45 ± 15 mPa.s

**Density at 20°C:** Ca 0.92

**Conventional solids content** (EN 827): 25 ±  
3%

**Application temperature:** 5 to 40°C

**Specific data:** Drying time: 10 to 15 min

## ■ FOR BEST RESULTS

- 12 months in the original, hermetically sealed packaging between 5 and 40°C.

## ■ CLEAN UP

Tools should be cleaned with **Primer 2001**, MEK or acetone before the sealant has completely cured. After curing, abrasion is necessary.

## ■ NOTE

The above technical information is based upon our best knowledge and we shall not be hold liable for any mistake, omission, lack of information due to technical changes between the issue of this TDS and the date the product was acquired. This technical information is strictly indicative and nonexhaustive as well as any information given over the phone. The end user must test the product with its substrate prior using it and verify that it is suitable for the application. If the end user needs more technical information on the product, he must contact the vendor or manufacturer prior using it for its recommended application or for a specific project.

Our liability is subject to the current law and regulations as well as the professional association standards and according to our general terms and conditions of sales.

**FOR INDUSTRIAL USE ONLY: BEFORE USE, REVIEW MATERIAL SAFETY DATA SHEET FOR FURTHER INFORMATION, INCLUDING CHRONIC HEALTH EFFECTS.**

**KEEP OUT OF REACH OF CHILDREN. NOT FOR INTERNAL CONSUMPTION. FOR INDUSTRIAL USE ONLY. KEEP CONTAINER TIGHTLY CLOSED. FOR MORE INFORMATION CONSULT MATERIAL SAFETY DATA SHEET.**



ECO  
FRIENDLY

Maxitech Inc. 7404 Sand Street.  
Fort Worth, TX, 76118

(817) 590 4472 | [www.maxitechusa.com](http://www.maxitechusa.com)